

Maximum Service Temperature of Commonly Applied Coatings

COATINGS	Maximum Service Temperature
<u>Zinc-Nickel Electroplating</u>	390° F / 210° C
<u>Zinc Electroplating</u>	390° F / 210° C
<u>Hot Dip Galvanizing</u>	660°F~700° F / 350°C~370° C
<u>Cadmium Electroplating</u>	450°F / 230°C
<u>TEFLON</u>	500° F / 260° C

